

## Axiall 4890 Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

**Material Notes:**

Non-lead stabilized, 85C rated automotive harness compound. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-4890-Flexible-PVC.php](http://www.lookpolymers.com/polymer_Axiall-4890-Flexible-PVC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 - 1.43 g/cc	1.39 - 1.43 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85 - 91	85 - 91	delayed; ASTM D-2240
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D-638
Elongation at Yield	219 %	219 %	Air Aging: 240 hours @ 125°C; 60 mil slabs; UL 1581
	300 %	300 %	ASTM D-638
100% Modulus	0.01362 GPa	1.975 ksi	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	188 °C	370 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China