

## Axiall LR-5009 Rigid PVC, Molding, All Colors

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Georgia Gulf LR-5009 is an economical high flow rigid PVC fittings compound designed for multi-cavity molds and large diameter fittings. This compound is characterized by excellent process ability, which includes color hold, regrind stability, and surface appearance. LR-5009 is NSF listed under Standard 14/61 for both potable water and DWV applications. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-LR-5009-Rigid-PVC-Molding-All-Colors.php](http://www.lookpolymers.com/polymer_Axiall-LR-5009-Rigid-PVC-Molding-All-Colors.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D-792
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	ASTM D-955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D-785
Tensile Strength, Yield	50.5 MPa	7320 psi	ASTM D-638
Tensile Modulus	2.96 GPa	430 ksi	ASTM D-638
Flexural Strength	88.3 MPa	12800 psi	ASTM D-790
Flexural Modulus	2.98 GPa	432 ksi	ASTM D-790
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D-256
	@Thickness 3.17 mm, Temperature -20.0 °C	@Thickness 0.125 in, Temperature -4.00 °F	
Gardner Impact	0.641 J/cm	1.20 ft-lb/in	ASTM D-256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
Gardner Impact	36.2 J	26.7 ft-lb	1/2" R Tup, 123 mil
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	76.00 °C	168.8 °F	ASTM D-648
Deflection Temperature at 1.8 MPa (264 psi)	72.00 °C	161.6 °F	ASTM D-648
Flammability, UL94	V-0	V-0	

Thermal Properties	Metric	English	Comments
<b>Descriptive Properties</b>			
Cell Classification, ASTM D-1784		12454-B	NSF std. 14
Flow Ratio (Distance/Wall Thickness, 390-400°F)		170	Georgia Gulf Test

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China