

## Axiall ProTherm® 4526 CPVC Rigid PVC, Molding

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Georgia Gulf ProTherm® 4526 CPVC is a pelletized injection molding compound designed for fittings. Typical applications are in potable water and chemical transfer systems especially where high resistance and/or elevated temperatures exist. 4526 has excellent processability, including thermal stability, flow, and surface appearance. ProTherm® 4526 is listed under NSF Standard 14 and Standard 61 and meets or exceeds ASTM D-1784 cell class 23447-B requirements. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-ProTherm-4526-CPVC-Rigid-PVC-Molding.php](http://www.lookpolymers.com/polymer_Axiall-ProTherm-4526-CPVC-Rigid-PVC-Molding.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.49 g/cc	1.49 g/cc	ASTM D-792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D-955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D-785
Tensile Strength, Yield	55.2 MPa	8010 psi	ASTM D-638
Tensile Modulus	3.41 GPa	495 ksi	ASTM D-638
Flexural Strength	89.6 MPa	13000 psi	ASTM D-790
Flexural Modulus	2.79 GPa	405 ksi	ASTM D-790
Izod Impact, Notched	1.33 J/cm @Thickness 6.35 mm	2.50 ft-lb/in @Thickness 0.250 in	ASTM D-256
Gardner Impact	20.3 J @Temperature 23.0 °C	15.0 ft-lb @Temperature 73.4 °F	1/2" R Tup, 180 mil

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	106.0 °C	222.8 °F	annealed; ASTM D-648
Deflection Temperature at 1.8 MPa (264 psi)	101.0 °C	213.8 °F	annealed; ASTM D-648
Vicat Softening Point	100 °C	212 °F	5kg Load at 50°C per Hour(annealed); ASTM D-1525A
Oxygen Index	44 %	44 %	ASTM D-2863

Descriptive Properties	Value	Comments
Cell Classification, ASTM D-1784	23447-B	
Flow Ratio (Distance/Wall Thickness, 410-425°F)	110	Georgia Gulf Test

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China