

## Axiall UV-6676 Rigid PVC, Molding

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Georgia Gulf UV-6676 is a weatherable, high flow injection molding compound, specially formulated for outdoor UV exposure. This compound was designed to be used in various accessory parts, such as fence post caps, rain gutter parts, deck parts, etc. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-UV-6676-Rigid-PVC-Molding.php](http://www.lookpolymers.com/polymer_Axiall-UV-6676-Rigid-PVC-Molding.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D-792
Linear Mold Shrinkage	0.0030 - 0.0040 cm/cm	0.0030 - 0.0040 in/in	ASTM D-955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	97	97	ASTM D-785
Tensile Strength, Yield	40.0 MPa	5800 psi	ASTM D-638
Tensile Modulus	2.21 GPa	320 ksi	ASTM D-638
Flexural Strength	65.5 MPa	9500 psi	ASTM D-790
Flexural Modulus	2.28 GPa	330 ksi	ASTM D-790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D-256
	@Thickness 3.17 mm, Temperature -20.0 °C	@Thickness 0.125 in, Temperature -4.00 °F	
	9.61 J/cm	18.0 ft-lb/in	ASTM D-256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
Gardner Impact	14.7 J	10.8 ft-lb	1/2" R Tup, 65 mil
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	72.00 °C	161.6 °F	ASTM D-648
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	ASTM D-648
Flammability, UL94	5VA	5VA	
Oxygen Index	35 %	35 %	ASTM D-2863

Thermal Properties	Metric	English	Value	Comments
Descriptive Properties			Value	Comments
Flow Ratio (Distance/Wall Thickness, 390-400°F)			230	Georgia Gulf Test
UL Weatherability Rating			F(2)	UL-746C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China