

Azdel SuperLite® SL551800-100 PP Resin Matrix / 55% Glass Fiber (4 mm Molded Thickness)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

AZDEL SuperLite® SL551800-100 is a low pressure, thermoformable, thermoplastic composite of polypropylene and long chopped glass fibers. Usually combined with outer layers as needed for the applications. Typically used in non-structural applications where a very high strength to weight ratio is required, such as:Automotive headlinersDoor panelsPackage shelvesOther interior trimPhysical properties apply only to bare SuperLite sheet and do not include surface films or scrim. Mechanical properties measured on flat plaques.Draw ratio is defined as the ratio of the maximum depth of the mold to the minimum distance across the open face of the mold at any given location and is measured on flat plaques.Information provided by Azdel.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azdel-SuperLite-SL551800-100-PP-Resin-Matrix-55-Glass-Fiber-4-mm-Molded-Thickness.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-----------------------|------------------|---|
| Specific Gravity | 0.490 g/cc | 0.490 g/cc | ASTM D3574 |
| Filler Content | 55 % | 55 % | ASTM D5630 |
| Thickness | 10500 - 11000 microns | 413 - 433 mil | Typical free lofted thickness after heating |
| Linear Mold Shrinkage | <= 0.00020 cm/cm | <= 0.00020 in/in | Typical, molds cut to zero |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------------------|----------------------|---|
| Tensile Strength at Break | 34.0 MPa | 4930 psi | ASTM D638 |
| Tensile Modulus | 3.60 GPa | 522 ksi | ASTM D638 |
| Flexural Strength | 20.0 MPa | 2900 psi | SAE J949 |
| Flexural Modulus | 1.75 GPa | 254 ksi | SAE J949 |
| Impact | 1500 | 1500 | Multi-axial in Newtons, at 23°C, at max. load, measured on flat plaques; ASTM D3763 |
| Impact Test | 5.80 J | 4.28 ft-lb | Multi-axial, at max. load; ASTM D3763 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| | 10.9 J | 8.04 ft-lb | Multi-axial, at failure, measured on flat plaques; ASTM D3763 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|----------------------|----------|
| Available Colors | Natural and Charcoal | |

| Draw Ratio Descriptive Properties | Max 1.5:1 Value | Comments |
|--------------------------------------|--------------------|----------|
|--------------------------------------|--------------------|----------|

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China