

## Azdel SuperLite® SL552000-100 PP Resin Matrix / 55% Glass Fiber (8 mm Molded Thickness)

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

AZDEL SuperLite® SL552000-100 is a low pressure, thermoformable, thermoplastic composite of polypropylene and long chopped glass fibers. Usually combined with outer layers as needed for the applications. Typically used in non-structural applications where a very high strength to weight ratio is required, such as:Automotive headlinersDoor panelsPackage shelvesOther interior trimPhysical properties apply only to bare SuperLite sheet and do not include surface films or scrim. Mechanical properties measured on flat plaques.Draw ratio is defined as the ratio of the maximum depth of the mold to the minimum distance across the open face of the mold at any given location and is measured on flat plaques.Information provided by Azdel.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Azdel-SuperLite-SL552000-100-PP-Resin-Matrix-55-Glass-Fiber-8-mm-Molded-Thickness.php](http://www.lookpolymers.com/polymer_Azdel-SuperLite-SL552000-100-PP-Resin-Matrix-55-Glass-Fiber-8-mm-Molded-Thickness.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.270 g/cc	0.270 g/cc	ASTM D3574
Filler Content	55 %	55 %	ASTM D5630
Thickness	12000 - 12500 microns	472 - 492 mil	Typical free lofted thickness after heating
Linear Mold Shrinkage	<= 0.00020 cm/cm	<= 0.00020 in/in	Typical, molds cut to zero

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	12.0 MPa	1740 psi	ASTM D638
Tensile Modulus	1.60 GPa	232 ksi	ASTM D638
Flexural Strength	4.00 MPa	580 psi	SAE J949
Flexural Modulus	0.500 GPa	72.5 ksi	SAE J949
Impact	1370	1370	Multi-axial in Newtons, at 23°C, at max. load, measured on flat plaques; ASTM D3763
Impact Test	9.30 J	6.86 ft-lb	Multi-axial, at max. load; ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	16.1 J	11.9 ft-lb	Multi-axial, at failure, measured on flat plaques; ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Descriptive Properties	Value	Comments
Available Colors	Natural and Charcoal	

Draw Ratio Descriptive Properties	Max 1.5:1 Value	Comments
--------------------------------------	--------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China