

Azoty Tarnow™ Alphalon™ 27C Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

A bright polyamide 6 grade of low viscosity suited for the production of compounds. Information provided by ATT Polymers™

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-Alphalon-27C-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ISO 1183
Relative Viscosity	2.6 - 2.8 cP	2.6 - 2.8 cP	1% in 96% H2SO4; ISO 307
Viscosity Test	150 cm ³ /g	150 cm ³ /g	0.5% in 96% H2SO4; ISO 307

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146

Component Elements Properties	Metric	English	Comments
TiO2	0.00 %	0.00 %	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.10 %	<= 0.10 %	Brabender

Descriptive Properties	Value	Comments
Black Points, 500 g	4	to 0.5 mm
Chip Shape	cylindrical	
Chip Size, mm	2.5	
Extract Content, %	internal	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China