

Azoty Tarnow™ TARNOFORM 500 UV POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

High flow injection molding grade based on Tarnoform 500 modified with carbon black giving best weathering stability. Information provided by Zakłady Azotowe w Tarnowie-Moscicach S.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-TARNOFORM-500-UV-POM.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.029 cm/cm	0.029 in/in	60x60x4
Linear Mold Shrinkage, Transverse	0.031 cm/cm	0.031 in/in	ISO 294-4
Melt Flow	23 g/10 min @Load 2.16 kg, Temperature 190 °C	23 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ISO 2039-2
Ball Indentation Hardness	142 MPa	20600 psi	358 N; ISO 2039-1
Tensile Strength, Yield	58.0 MPa	8410 psi	ISO 527
Elongation at Break	14 %	14 %	ISO 527
Flexural Strength	61.0 MPa	8850 psi	ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	1A; ISO 180
Charpy Impact, Notched	0.550 J/cm ²	2.62 ft-lb/in ²	1eA; ISO 179

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.48 J/g-°C	0.354 BTU/lb-°F	
Melting Point	167 °C	333 °F	10°C/min.; ISO 3146
Maximum Service Temperature, Air	100 °C	212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	147 °C	297 °F	ISO 75
Vicat Softening Point	147 °C	297 °F	50 N; ISO 306
	HB	HB	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	3.9	3.9	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243
Dissipation Factor	0.0085	0.0085	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	IEC 112

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 230 °C	356 - 446 °F	Barrel temperature
Mold Temperature	60.0 - 120 °C	140 - 248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China