

## Azoty Tarnow™ Tarnamid® T-27 GF10 GB20 Polyamide 6 - Glass Beads Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Bead Filled

### Material Notes:

10% Glass fiber and 20% glass beads reinforced, medium viscosity injection molding grade, also used for compounding, for production of monofilament, bristles and fibers. Tarnamid® has the following main properties: High mechanical strength, rigidity and hardness High impact strength High vibration damping capacity Good fatigue strength Very good sliding properties, abrasion resistance, low coefficient of friction High thermal resistance, admissible temperature of continuous operation from -60°C to +150°C High chemical resistance, particularly to organic solvents, oils, lubricants and fuels Considerable moisture absorption influencing mechanical and electrical properties Self-extinguishing properties (fire retardant properties) Good electro-insulating properties Good optical properties, relatively good transparency of molded pieces with thickness below 3.2 mm made from natural Tarnamid® (not dyed and not compounded) Can be used for the production of goods coming into contact with food (grades fulfilling requirement of European Union Directive No 2002/72/EEC) with latest amendments Information provided by Azoty Tarnow™.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Azoty-Tarnow-Tarnamid-T-27-GF10-GB20-Polyamide-6-Glass-Beads-Reinforced.php](http://www.lookpolymers.com/polymer_Azoty-Tarnow-Tarnamid-T-27-GF10-GB20-Polyamide-6-Glass-Beads-Reinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ISO 1183
Water Absorption	1.3 %	1.3 %	ISO 62
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0070 cm/cm	0.0070 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.013 cm/cm	0.013 in/in	ISO 294-4
Melt Flow	50 g/10 min	50 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 275 °C	@Load 11.0 lb, Temperature 527 °F	

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	200 MPa	29000 psi	ISO 2039-1
	@Load 36.5 kg	@Load 80.5 lb	
Tensile Strength	100 MPa	14500 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Tensile Modulus	5.40 GPa	783 ksi	ISO 527
Flexural Strength	<= 150 MPa	<= 21800 psi	3.5% flexure; ISO 178
Flexural Modulus	4.80 GPa	696 ksi	ISO 178

Charpy Impact Unnotched Mechanical Properties	4.50 J/cm <sup>2</sup> Metric	21.4 ft-lb/in <sup>2</sup> English	ISO 179 1e1 Comments
Charpy Impact, Notched	0.450 J/cm <sup>2</sup>	2.14 ft-lb/in <sup>2</sup>	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75
Vicat Softening Point	210 °C @Load 5.10 kg	410 °F @Load 11.2 lb	ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 290 °C	446 - 554 °F	
Mold Temperature	60.0 - 120 °C	140 - 248 °F	80 - 90°C is recommended
Drying Temperature	75.0 - 100 °C @Time 7200 - 14400 sec	167 - 212 °F @Time 2.00 - 4.00 hour	
Moisture Content	<= 0.10 %	<= 0.10 %	
Injection Pressure	80.0 - 130 MPa	11600 - 18900 psi	80 MPa is recommended

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China