

Azoty Tarnow™ Tarnamid® T-27 TF10 Polyamide 6 - Improved Slip Properties

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , MoS2 Filled

Material Notes:

Medium viscosity injection molding grade, also used for compounding, for production of monofilament, bristles and fibers. Low wear and low friction grade, contains molybdenum disulfide, PTFE. Tarnamid® has the following main properties: High mechanical strength, rigidity and hardness. High impact strength. High vibration damping capacity. Good fatigue strength. Very good sliding properties, abrasion resistance, low coefficient of friction. High thermal resistance, admissible temperature of continuous operation from -60°C to +150°C. High chemical resistance, particularly to organic solvents, oils, lubricants and fuels. Considerable moisture absorption influencing mechanical and electrical properties. Self-extinguishing properties (fire retardant properties). Good electro-insulating properties. Good optical properties, relatively good transparency of molded pieces with thickness below 3.2 mm made from natural Tarnamid® (not dyed and not compounded). Can be used for the production of goods coming into contact with food (grades fulfilling requirement of European Union Directive No 2002/72/EEC) with latest amendments. Information provided by Azoty Tarnow™.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-Tarnamid-T-27-TF10-Polyamide-6-Improved-Slip-Properties.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ISO 1183
Linear Mold Shrinkage, Flow	0.014 cm/cm	0.014 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.018 cm/cm	0.018 in/in	ISO 294-4
Melt Flow	60 g/10 min @Load 5.00 kg, Temperature 275 °C	60 g/10 min @Load 11.0 lb, Temperature 527 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	140 MPa @Load 36.5 kg	20300 psi @Load 80.5 lb	ISO 2039-1
Tensile Strength	75.0 MPa	10900 psi	ISO 527
Elongation at Break	13 %	13 %	ISO 527
Tensile Modulus	3.00 GPa	435 ksi	ISO 527
Flexural Strength	<= 83.0 MPa	<= 12000 psi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179 1eU
Charpy Impact, Notched	0.500 J/cm²	2.38 ft-lb/in²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	221 °C Metric	430 °F English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	ISO 75
Vicat Softening Point	135 °C @Load 5.10 kg	275 °F @Load 11.2 lb	ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 290 °C	446 - 554 °F	
Mold Temperature	60.0 - 120 °C	140 - 248 °F	80 - 90°C is recommended
Drying Temperature	75.0 - 100 °C @Time 7200 - 14400 sec	167 - 212 °F @Time 2.00 - 4.00 hour	
Moisture Content	<= 0.10 %	<= 0.10 %	
Injection Pressure	80.0 - 130 MPa	11600 - 18900 psi	80 MPa is recommended

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China