

## BASF 4,7,10-Trioxatridecane-1,13-Diamine

Category : Fluid

**Material Notes:**

Formula: C<sub>9</sub>H<sub>12</sub>O<sub>2</sub>CAS: 4246-51-9Description: TTD is a colorless to yellow liquid, with an amine-like odor. It is also miscible with water in all proportions.Synonyms: TTDApplications: Intermediate used in Hardeners for epoxy resins and Cross-linking agents for epoxy resinInformation provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-4710-Trioxatridecane-113-Diamine.php](http://www.lookpolymers.com/polymer_BASF-4710-Trioxatridecane-113-Diamine.php)

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in <sup>3</sup>	
Molecular Weight	220.3 g/mol	220.3 g/mol	

Thermal Properties	Metric	English	Comments
Melting Point	-32.0 °C	-25.6 °F	
Boiling Point	146 - 148 °C	295 - 298 °F	
Flash Point	139 °C	282 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.20 %	<= 0.20 %	DIN 51 777

Descriptive Properties	Value	Comments
Assay	>98%	
Color	<40	APHA, DIN EN 1557
Ignition Temperature	260°C	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China