

## BASF Capron® 5202 HS Blend Nylon 66 (Dry) (discontinued \*\*)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

### Material Notes:

Capron 5202 HS Blend is a blended, unfilled, heat stabilized, nylon 6,6, injection molding compound. It is also available in natural and pigmented versions. It combines strength and stiffness as well as excellent chemical resistance. The addition of heat stabilizer system extends the retention of properties at elevated temperatures. Capron 5202 HS Blend is generally recommended for slightly higher temperature and stiffness requirements, such as engine components, power tool guides, straps and other hardware. Data provided by Allied Signal. Processing: Max. water content 0.25%. Product is supplied in sealed containers and drying is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 85°C (185 °F). Is recommended. Drying time is dependent on moisture level. Melt Temperature: 280-305 degC (536-581 degF). Mold Temperature: 80-95 degC (176-203 degF). Injection and Packing Pressure: 35-125 bar (500-1500psi) A mold temperature of 80-95 degC (176-203 degF) is recommended, but temperatures of as low as 45 degC (113 degF) and as high as 105 degC (221 degF) can be used where applicable. Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off. Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid ® line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Capron-5202-HS-Blend-Nylon-66-Dry-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_BASF-Capron-5202-HS-Blend-Nylon-66-Dry-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ISO data
Moisture Absorption at Equilibrium	2.5 %	2.5 %	50% RH; 23°C; ISO data
Water Absorption at Saturation	8.5 %	8.5 %	in water; 23°C; ISO data
Viscosity Measurement	55	55	Formic Acid Viscosity; ISO data
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM Data MD

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	ASTM value at 50 mm/min.
	86.0 MPa	12500 psi	ISO value at 50 mm/min.
Elongation at Break	15 %	15 %	Nominal
	15 %	15 %	Nominal
Elongation at Yield	5.0 %	5.0 %	ISO Value at 50 mm/min.
	5.0 %	5.0 %	ASTM Value at 50 mm/min.
Flexural Yield Strength	130 MPa	18900 psi	ASTM Data

Mechanical Properties	Metric	English	Comments
Poissons Ratio	0.35	0.35	ISO data

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ASTM and ISO test
Deflection Temperature at 1.8 MPa (264 psi)	77.0 °C	171 °F	ASTM Data
	80.0 °C	176 °F	ISO data
Flammability, UL94	V-2	V-2	
	@Thickness 0.700 mm	@Thickness 0.0276 in	
	V-2	V-2	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Drying Temperature	85.0 °C	185 °F	See Materials Notes

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China