

BASF Capron® 8232G 25% Glass-Filled Nylon 6 (Conditioned) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Capron 8232G is a 25% glass fiber reinforced nylon 6 molding compound offering excellent strength, stiffness, high temperature performance and dimensional stability. Its resistance to creep under load is excellent along with its chemical resistance to greases, oils and hydrocarbons. Capron 8232G is ideally suited for applications such as safety helmet parts, washers, gears, engine and motor parts, chutes, and higher temperature environments. Data provided by Allied Signal. Processing: Max. water content 0.16%. Product is supplied in sealed containers and drying is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 85°C (185 °F). Is recommended. Drying time is dependent on moisture level. Melt Temperature: 250-280 degC (482-536 degF). Mold Temperature: 80-95 degC (176-203 degF). Injection and Packing Pressure: 35-125 bar (500-1500psi) This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics critical, a mold surface temperature of 80-95 degC (176-203 degF) is required. Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off. Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 3.5 bar (50 psi) is recommended to minimize glass fiber breakage. Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid ® line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Capron-8232G-25-Glass-Filled-Nylon-6-Conditioned-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	(Dry)
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM Data MD (Dry)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	105 MPa	15200 psi	ASTM data at 5 mm/min.
Flexural Yield Strength	140 MPa	20300 psi	ASTM Data
Flexural Modulus	3.86 GPa	560 ksi	ASTM Data

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)

Processing Properties	Metric	English	Comments
Processing Temperature	275 °C	527 °F	See Materials Notes
Mold Temperature	95.0 °C	203 °F	See Materials Notes

Drying Temperature
Processing Properties

85.0 °C
Metric

185 °F
English

See Materials Notes
Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China