

BASF Capron® 8232G HS FR 25% Glass-Filled Nylon 6 (Dry) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass Fiber Filled, Flame Retardant

Material Notes:

Capron 8232G HS FR is a 25% glass fiber reinforced, heat stabilized, flame retardant nylon 6 injection molding compound exhibiting excellent melt stability characteristics. It combines flame retardant ability with an excellent balance of high strength, stiffness and heat distortion temperature. Capron 8232G HS FR is generally recommended for applications such as connectors, terminal blocks, switches and receptacles, coil bobbins, and appliance housings. Data provided by Allied Signal. Processing: Max. water content 0.16%. Product is supplied in sealed containers and drying is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 85°C (185 °F). Is recommended. Drying time is dependent on moisture level. Melt Temperature: 250-280 degC (482-536 degF). Mold Temperature: 80-95 degC (176-203 degF). Injection and Packing Pressure: 35-125 bar (500-1500psi) This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics critical, a mold surface temperature of 80-95 degC (176-203 degF) is required. Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off. Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 3.5 bar (50 psi) is recommended to minimize glass fiber breakage. Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid ® line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Capron-8232G-HS-FR-25-Glass-Filled-Nylon-6-Dry-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.62 g/cc	0.0585 lb/in ³	ISO data
Moisture Absorption at Equilibrium	1.1 %	1.1 %	50% RH; 23°C; ISO data
Water Absorption at Saturation	4.0 %	4.0 %	in water; 23°C; ISO data
Viscosity Measurement	50	50	Formic Acid Viscosity; ISO data
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM Data MD

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	157 MPa	22800 psi	ISO value at 5mm/min.
	160 MPa	23200 psi	ASTM data at 5 mm/min.
Elongation at Break	3.0 %	3.0 %	ISO, 5 mm/minl
	3.0 %	3.0 %	ASTM, 5 mm/minl
Flexural Yield Strength	215 MPa	31200 psi	ASTM Data
Flexural Modulus	8.965 GPa	1300 ksi	ASTM Data

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ASTM and ISO test
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ASTM Data
Flammability, UL94	V-0	V-0	
	@Thickness 0.840 mm	@Thickness 0.0331 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	
	5VA	5VA	
	@Thickness 2.50 mm	@Thickness 0.0984 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	ISO data
Dielectric Strength	29.0 kV/mm	737 kV/in	ISO data

Processing Properties	Metric	English	Comments
Processing Temperature	275 °C	527 °F	See Materials Notes
Mold Temperature	80.0 - 95.0 °C	176 - 203 °F	
	95.0 °C	203 °F	See Materials Notes
Drying Temperature	85.0 °C	185 °F	See Materials Notes
Injection Pressure	3.45 - 10.3 MPa	500 - 1500 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China