

BASF Capron® 8333G Impact Modified, 33% Glass-Filled Nylon 6 (Conditioned) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Filled, Impact Grade

Material Notes:

Capron 8333G is a 33% glass reinforced nylon 6 modified compound developed for applications requiring improved dry as molded toughness in combination with a balance of strength, stiffness, and excellent moldability/surface aesthetics. It maintains its inherent chemical resistance to greases, oils and hydrocarbons. It is also available in natural, heat stabilized, and pigmented versions. Capron 8333G is generally recommended for applications such as include power tool and chain saw housings components. Data provided by Allied Signal. Processing: Max. water content 0.12%. Product is supplied in sealed containers and drying is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 85°C (185 °F). Is recommended. Drying time is dependent on moisture level. Melt Temperature: 270-295 degC (518-563 degF). Mold Temperature: 80-95 degC (176-203 degF). Injection and Packing Pressure: 35-125 bar (500-1500psi) This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics critical, a mold surface temperature of 80-95 degC (176-203 degF) is required. Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off. Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 3.5 bar (50 psi) is recommended to minimize glass fiber breakage. Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid ® line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Capron-8333G-Impact-Modified-33-Glass-Filled-Nylon-6-Conditioned-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	(Dry)
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM Data MD (Dry)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	85.0 MPa	12300 psi	ASTM data at 5 mm/min.
	86.0 MPa	12500 psi	ISO value at 5mm/min.
Elongation at Break	8.0 %	8.0 %	ISO, 5 mm/minl
	8.0 %	8.0 %	ASTM, 5 mm/minl
Flexural Yield Strength	140 MPa	20300 psi	ASTM Data
Flexural Modulus	4.48 GPa	650 ksi	ASTM Data

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Drying Temperature	85.0 °C	185 °F	See Materials Notes

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China