

BASF Capron® HPN 9315G HS BK-102 Impact Modified, 15% Glass-Filled Nylon 6 (Conditioned) (discontinued **)<

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass Filled, Impact Grade

Material Notes:

Capron HPN 9315G HS BK-102 is a 15% glass reinforced impact modified, heat stabilized, pigmented black, nylon 6 injection molding grade resin. It is in the High Productivity Nylon Series developed for applications requiring superior dry-as-molded (DAM) toughness, improved impact resistance and reduced cycle times. It also has excellent surface appearance and is available in natural, heat stabilized, and pigmented versions. It combines the strength, toughness and stiffness of a modified glass reinforced nylon 6 resin. It maintains its inherent chemical resistance to greases, oils and hydrocarbons. Capron HPN 9315G HS BK-102 is generally recommended for applications such as power tool and chain saw and vacuum housings. Data provided by Allied Signal. Processing: Max. water content 0.12%. Product is supplied in sealed containers and drying is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 85°C (185 °F). Is recommended. Drying time is dependent on moisture level. Melt Temperature: 270-295 degC (518-563 degF). Mold Temperature: 80-95 degC (176-203 degF). Injection and Packing Pressure: 35-125 bar (500-1500psi) This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics critical, a mold surface temperature of 80-95 degC (176-203 degF) is required. Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off. Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 3.5 bar (50 psi) is recommended to minimize glass fiber breakage. Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid ® line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Capron-HPN-9315G-HS-BK-102-Impact-Modified-15-Glass-Filled-Nylon-6-Conditioned-nbspdiscontinued-It.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	(Dry)
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM Data MD (Dry)

Mechanical Properties	Metric	English	Comments
Flexural Yield Strength	100 MPa	14500 psi	ASTM Data

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)

Processing Properties	Metric	English	Comments
Drying Temperature	85.0 °C	185 °F	See Materials Notes

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China