

BASF Elastollan 560 D TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties and a high abrasion resistance. Typical

Applications: Heel top-pieces, castor tyres and parts requiring a high durability. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-560-D-TPUR.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	61	61	ISO 686
Tensile Strength	45.0 MPa	6530 psi	ISO 37
Elongation at Break	450 %	450 %	ISO 37
Tear Strength	180 kN/m	1030 pli	DIN ISO 34-1/Bb
Abrasion	30	30	[mm³ ISO 4649

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Injection molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China