

BASF Elastollan B 60 A ESD TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties, outstanding wear resistance, high tensile strength, good damping and resilience performance and superior low temperature flexibility. Typical Applications: Sport-shoe soles and accessories, ski-boot shells, technical moldings, e.g. seals, castor tyres and tubing. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-B-60-A-ESD-TPUR.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ISO 868
Tensile Strength	20.0 MPa	2900 psi	ISO 37
	20.0 MPa	2900 psi	after storage in water at 80°C for 42 days; ISO 37
	1.00 MPa	145 psi	ISO 37
	@Strain 20.0 %	@Strain 20.0 %	
	2.50 MPa	363 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
Elongation at Break	6.50 MPa	943 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
	800 %	800 %	ISO 37
	900 %	900 %	after storage in water at 80°C for 42 days; ISO 37
Charpy Impact, Notched	NB	NB	DIN EN ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	DIN EN ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tear Strength	40.0 kN/m	228 pli	DIN ISO 34-1/Bb
Abrasion	120	120	[mm ³]; ISO 4649
	20 %	20 %	

Compression Set Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	ISO 815 Comments
	30 %	30 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	Injection molding
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Injection molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China