

BASF Elastollan® C-90A Polyester Type Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Processed by extrusion or injection molding. Elastollan C series of products are polyester-based thermoplastic polyurethanes that exhibit very good hydrolytic stability. They also exhibit excellent oil, fuel and solvent resistance. These products can be injection and blow molded and extruded. As with all TPU products this grade must be dried prior to processing. Property values below are typical values based on test samples cured 20 hours at 100°C before testing. Information provided by BASF Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-C-90A-Polyester-Type-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	ASTM D2240
Hardness, Shore D	41	41	ASTM D2240
Tensile Strength, Ultimate	41.0 MPa	5950 psi	ASTM D412
Tensile Strength, Yield	10.0 MPa @Strain 100 %	1450 psi @Strain 100 %	ASTM D-412
	22.0 MPa @Strain 300 %	3190 psi @Strain 300 %	ASTM D-412
Elongation at Break	550 %	550 %	ASTM D412
Tear Strength	120 kN/m	685 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	25	25	H-18 wheel; ASTM D-1044.
Tensile Set	50 %	50 %	at break; ASTM D-412

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 600 V	>= 600 V	DIN/IRC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China