

BASF Elastollan S 60 D TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties and wear resistance, good damping characteristics and a high resilience performance. Typical Applications: Shoe-soles, top pieces, tubes, technical parts e.g. castor tyres. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-S-60-D-TPUR.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ISO 686
Tensile Strength	45.0 MPa	6530 psi	ISO 37
	15.0 MPa	2180 psi	ISO 37
	@Strain 20.0 %	@Strain 20.0 %	
	18.0 MPa	2610 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	34.0 MPa	4930 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	500 %	500 %	ISO 37
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	DIN EN ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	DIN EN ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tear Strength	170 kN/m	970 pli	DIN ISO 34-1/Bb
Abrasion	25	25	[mm³; ISO 4649
Compression Set	40 %	40 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	50 %	50 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 240 °C	347 - 464 °F	Injection molding
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Injection molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China