

BASF Lupranate® 219 Isocyanate Modified MDI

Category : Fluid

Material Notes:

Description: Lupranate® 219 Isocyanate is a liquid carbodiimide modified 4,4'-diphenylmethane diisocyanate. Lupranate 219 Isocyanate is a light-colored alternative to Lupranate MM103 Isocyanate. A combination of consistent color and good shelf-stability lends this product to applications such as flexible and rigid elastomers, coatings, and prepolymers. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-219-Isocyanate-Modified-MDI.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Viscosity	40 cP	40 cP	
Vapor Pressure	<= 1.33e-8 bar @Temperature 25.0 °C	<= 0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	>= 200 °C	>= 392 °F	

Descriptive Properties	Value	Comments
Color	<225 Pale Yellow	APAH
Composition	NCO content	0.292

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China