

BASF Lupranate® 223 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 223 Isocyanate is a low viscosity derivative of both pure-MDI and polymeric-MDI. With a functionality of approximately 2.2, this isocyanate can be formulated into applications that require good flow and working time such as 1- and 2-component adhesives and coatings. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-223-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Viscosity	140 cP	140 cP	
Vapor Pressure	2.67e-7 bar @Temperature 25.0 °C	0.000200 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	>= 200 °C	>= 392 °F	

Descriptive Properties	Value	Comments
Color	Light Brown	
Composition	NCO content	0.275

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China