

BASF Lupranate® 233 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 233 Isocyanate is a stable liquid polymeric MDI prepolymer. When used in molded flexible foams, Lupranate 233 Isocyanate demonstrates the ability to combine softness of foam with good tear strength. It offers low temperature stability, wide processing latitude and the potential for lower scrap rates. It is also used in the production of semiflexible and integral skin foams, elastomers, coatings and adhesives. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-233-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Viscosity	175 cP	175 cP	
Vapor Pressure	2.67e-7 bar @Temperature 25.0 °C	0.000200 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	>= 200 °C	>= 392 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Composition	NCO content	0.254

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China