

BASF Lupranate® 234 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 234 Isocyanate is a low functionality (approximately 2.3) low viscosity polymeric MDI with high 2,4'-MDI isomer content. Lupranate® 234 Isocyanate exhibits excellent low temperature stability. This product will remain a liquid for several days at 0°C. When properly formulated, it is suitable for applications such as elastomers, potting compounds, adhesives, sealants, and carpet backing, as well as integral skin, semi-flexible and packaging foams. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-234-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	
Viscosity	50 cP	50 cP	
Vapor Pressure	4.00e-7 bar @Temperature 25.0 °C	0.000300 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	199 °C	390 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Composition	NCO content	0.32

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China