

BASF Lupranate® 241 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 241 Isocyanate is a low functionality (approximately 2.3) low viscosity polymeric MDI with high 2,4'-MDI isomer content. Lupranate® 241 Isocyanate exhibits excellent low temperature stability. This product will remain a liquid for several days at 0°C. When properly formulated, it is suitable for applications such as elastomers, potting compounds, adhesives, sealants, and carpet backing, as well as integral skin, semiflexible and packaging foams. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-241-Isocyanate.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------------------------------|---------------------------------------|----------|
| Density | 1.22 g/cc | 0.0441 lb/in ³ | |
| Viscosity | 26 cP | 26 cP | |
| Vapor Pressure | 4.00e-7 bar @Temperature 25.0 °C | 0.000300 torr @Temperature 77.0 °F | |

| Thermal Properties | Metric | English | Comments |
|--------------------|-------------------------------------|-----------------------------------|----------|
| Boiling Point | >= 190 °C @Pressure 0.000667 MPa | >= 374 °F @Pressure 0.0967 psi | |
| Flash Point | 199 °C | 390 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-------------|----------|
| Color | Brown | |
| Composition | NCO content | 0.326 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China