

BASF Lupranate® 5050 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 5050 Isocyanate is a prepolymer based on a modified, pure MDI. The intermediate free-NCO and slightly enhanced functionality of Lupranate 5050 isocyanate has benefited the formulation of flexible coatings, sealants, potting compounds, and various elastomers. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-5050-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Viscosity	335 cP	335 cP	
Vapor Pressure	<= 1.33e-8 bar @Temperature 25.0 °C	<= 0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	200 °C	392 °F	

Descriptive Properties	Value	Comments
Color	Yellow	
Composition	NCO content	0.215

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China