

## BASF Lupranate® 5060 Isocyanate

Category : Fluid

**Material Notes:**

Description: Lupranate® 5060 Isocyanate is a low functional prepolymer based on monomeric MDI. Lupranate® 5060 isocyanate is suitable for use in a broad range of flexible, semi-flexible, and cast urethane elastomers. In addition, the 15.5% free-NCO of this prepolymer proves useful in fixed-ratio polyurethane and polyurea applications. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Lupranate-5060-Isocyanate.php](http://www.lookpolymers.com/polymer_BASF-Lupranate-5060-Isocyanate.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	
Viscosity	1000 cP	1000 cP	
Vapor Pressure	1.33e-8 bar @Temperature 25.0 °C	0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	200 °C	392 °F	

Descriptive Properties	Value	Comments
Color	Clear	
Composition	NCO content	0.155

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China