

BASF Lupranate® 8020 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 8020 Isocyanate is an 80:20 weight percent combination of toluene diisocyanate (TDI) and polymethylene polyphenylisocyanate (polymeric MDI). This product is used in the preparation of polyurethane foams, prepolymers, and elastomers and should be thoroughly mixed before using to ensure uniform isomer distribution and reactivity. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-8020-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	
Vapor Pressure	0.0000133 bar @Temperature 25.0 °C	0.00998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Flash Point	132 °C	270 °F	

Descriptive Properties	Value	Comments
Acidity, as HCl	<0.009 %	as HCl, STI 8244
Color	Brown	
Composition	NCO content	43.6-45.4%, STI 8243

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China