

## BASF Lupranate® M Isocyanate

Category : Fluid

**Material Notes:**

Description: Lupranate® M Isocyanate, a solid at room temperature, is essentially pure 4,4'-diphenylmethane diisocyanate, having a functionality of 2.0. Lupranate M Isocyanate is used in the isocyanate component for the preparation of elastomeric and thermoplastic polyurethanes, flexible and semi-flexible integral skin foams, adhesives, sealants and coatings. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Lupranate-M-Isocyanate.php](http://www.lookpolymers.com/polymer_BASF-Lupranate-M-Isocyanate.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	
Vapor Pressure	4.00e-7 bar @Temperature 25.0 °C	0.000300 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	38.5 °C	101 °F	
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	199 °C	390 °F	

Descriptive Properties	Value	Comments
Color	White to Light Yellow	
Composition	2,4' Isomer	0.02
	Hydrolyzable Chlorine	<20.0%
	NCO content	0.335
Purity	0.995	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China