

BASF Lupranate® M20FB Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® M20FB is a polymeric MDI with a functionality of approximately 2.7. Lupranate® M20FB has faster reactivity than polymeric MDI currently used in the wood panel industry. This enhancement is designed for the wood industry where faster productivity is desired. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-M20FB-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	
Viscosity	200 cP	200 cP	
Vapor Pressure	1.33e-8 bar @Temperature 25.0 °C	0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	>= 200 °C	>= 392 °F	

Descriptive Properties	Value	Comments
Color	Dark Brown	
Composition	Hydrolyzable Chlorine	<0.025%
	NCO content	0.315

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China