

BASF Lupranate® M20SB Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® M20SB is a polymeric MDI with a functionality of approximately 2.7. Lupranate® M20SB is a highly efficient, field-proven binder for cellulosic materials in products such as: Oriented Strand Board (OSB), Strawboard, Medium Density Fiberboard (MDF), Particle Board, and Bagasse Board. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-M20SB-Isocyanate.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------------------------------|---|----------|
| Density | 1.23 g/cc | 0.0444 lb/in ³ | |
| Viscosity | 200 cP | 200 cP | |
| Vapor Pressure | 1.33e-8 bar @Temperature 25.0 °C | 0.00000998 torr @Temperature 77.0 °F | |

| Thermal Properties | Metric | English | Comments |
|--------------------|-------------------------------------|-----------------------------------|----------|
| Boiling Point | >= 190 °C @Pressure 0.000667 MPa | >= 374 °F @Pressure 0.0967 psi | |
| Flash Point | >= 200 °C | >= 392 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------------------|----------|
| Color | Dark Brown | |
| Composition | Hydrolyzable Chlorine | <0.025% |
| | NCO content | 0.315 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China