

BASF Lupranate® MM103 Isocyanate Modified MDI

Category : Fluid

Material Notes:

Description: Lupranate® MM103 is a liquid carbodiimide modified 4,4'-diphenylmethane diisocyanate. Lupranate MM103 serves as the isocyanate component in the production of microcellular urethane elastomers. This product also may be used in combination with high molecular weight polyether polyols for the preparation of high grade flexible, semi-flexible and integral skin foam. It is also used in the preparation of prepolymers for elastomer, sealant, adhesive and coating applications. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-MM103-Isocyanate-Modified-MDI.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	
Viscosity	40 cP	40 cP	
Vapor Pressure	<= 1.33e-8 bar @Temperature 25.0 °C	<= 0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	199 °C	390 °F	

Descriptive Properties	Value	Comments
Color	Light Yellow	
Composition	Hydrolyzable Chlorine	<30.0%
	NCO content	0.295

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China