

BASF Novolen® 1184 L Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Nucleated grade with high processing stability containing antistatic for thermoformed parts. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Novolen-1184-L-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	
Water Absorption	0.10 %	0.10 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Linear Mold Shrinkage, Flow	0.013 cm/cm	0.013 in/in	
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.0 MPa	5080 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	10 %	10 %	
Tensile Modulus	1.60 GPa	232 ksi	
Charpy Impact Unnotched	14.0 J/cm ²	66.6 ft-lb/in ²	
	1.60 J/cm ² @Temperature -30.0 °C	7.61 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	
	0.170 J/cm ² @Temperature -30.0 °C	0.809 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	135 µm/m-°C @Temperature 20.0 °C	75.0 µin/in-°F @Temperature 68.0 °F	
Melting Point	163 °C	325 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	50.0 °C	124 °F	
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	
Vicat Softening Point	94.0 °C	201 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	
Dielectric Constant	2.3	2.3	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Constant	2.3	2.3	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	140 kV/mm	3560 kV/in	
Dissipation Factor	0.000070	0.000070	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0020	0.0020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China