

BASF Novolen® 2348 M Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Novolen-2348-M-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	
Water Absorption	0.10 %	0.10 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Linear Mold Shrinkage, Flow	0.013 cm/cm	0.013 in/in	
Melt Flow	11 g/10 min	11 g/10 min	
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	7.0 %	7.0 %	
Tensile Modulus	1.40 GPa	203 ksi	
Charpy Impact Unnotched	NB	NB	
	8.00 J/cm ²	38.1 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	
	0.250 J/cm ²	1.19 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	150 µm/m-°C	83.3 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	163 °C	325 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (264 psi)	90.0 °C	194 °F	
Deflection Temperature at 1.8 MPa (264 psi)	53.0 °C	127 °F	
Vicat Softening Point	68.0 °C	154 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	
Dielectric Constant	2.3	2.3	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	140 kV/mm	3560 kV/in	
Dissipation Factor	0.00081	0.00081	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0020	0.0020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China