

BASF Petra® 7010 WT 7729 15% Glass Filled PET

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 20% Glass Reinforced

Material Notes:

Description: Petra 7010 WT7729 is a 15% glass fiber reinforced, pigmented white injection molding compound based on post-consumer recycle polyethylene terephthalate. Formulated for superior surface aesthetics, it exhibits excellent melt stability and high flow over a broad range of processing conditions. The combination of high strength and dimensional stability enable its use in structural applications designed for metal. Application: Petra 7010 WT7729 is recommended for applications such as appliance door handles and knobs. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Petra-7010-WT-7729-15-Glass-Filled-PET.php

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ISO 527
Elongation at Break	1.5 %	1.5 %	ISO 527
Flexural Modulus	6.80 GPa	986 ksi	ISO 178
Charpy Impact Unnotched	1.50 J/cm ² @Temperature 5.00 °C	7.14 ft-lb/in ² @Temperature 41.0 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	245 °C	473 °F	ASTM D3418
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 °C	536 - 572 °F	
Mold Temperature	100 - 110 °C	212 - 230 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	0.20 %	0.20 %	

Descriptive Properties	Value	Comments
Color	WT 7792	

Descriptive Properties

Value *America*

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China