

BASF Pluracol® 736 Rigid Polyol

Category : Fluid

Material Notes:

Description: Pluracol® 736 polyol is an aromatic initiator-based polyol which can be used in a variety of rigid foam formulations. This polyol can be reacted with crude MDI, crude TDI or TDI quasiprepolymers. Formulations containing Pluracol 736 can be utilized for foaming building and door panels, refrigerators and freezers, and other insulating products such as portable ice chests and water coolers. Pluracol 736 has good compatibility with common foam ingredients and improves the processability of low density foam formulations. Pluracol 736 is not recommended for use in quasi-prepolymer preparations. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Pluracol-736-Rigid-Polyol.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
	@Temperature 70.0 °C	@Temperature 158 °F	
	1.03 g/cc	0.0372 lb/in ³	
	@Temperature 60.0 °C	@Temperature 140 °F	
	1.04 g/cc	0.0376 lb/in ³	
	@Temperature 40.0 °C	@Temperature 104 °F	
Viscosity	400 cP	400 cP	
	@Temperature 60.0 °C	@Temperature 140 °F	
	415 cP	415 cP	
	@Temperature 70.0 °C	@Temperature 158 °F	
	14500 cP	14500 cP	
	@Temperature 40.0 °C	@Temperature 104 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.050 %	<= 0.050 %	STI 3062

Descriptive Properties	Value	Comments
Color	Brown Liquid	
Hydroxyl Number	380 - 400 mg KOH/g	STI 3007/3162

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China