

## BASF Pluracol® TP 2540 Specialty Polyol

Category : Fluid

### Material Notes:

Description: Pluracol® TP polyols are a series of four tri-functional polyols formed by adding propylene oxide to a trimethylol propane nucleus. All Pluracol TP polyols are used in flexible and rigid polyurethane foams, coatings, adhesives, sealants and elastomers. Various members may be used in the preparation of prepolymers as cross-linking agents or as polyol reactants in one-shot systems. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Pluracol-TP-2540-Specialty-Polyol.php](http://www.lookpolymers.com/polymer_BASF-Pluracol-TP-2540-Specialty-Polyol.php)

Physical Properties	Metric	English	Comments
Density	0.979 g/cc	0.0354 lb/in <sup>3</sup>	
	@Temperature 60.0 °C	@Temperature 140 °F	
	1.00 g/cc	0.0361 lb/in <sup>3</sup>	
	@Temperature 37.8 °C	@Temperature 100 °F	
	1.01 g/cc	0.0365 lb/in <sup>3</sup>	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	50 cP	50 cP	
	@Temperature 60.0 °C	@Temperature 140 °F	
	125 cP	125 cP	
	@Temperature 37.8 °C	@Temperature 100 °F	
	400 cP	400 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.16 J/g-°C	0.277 BTU/lb-°F	
Thermal Conductivity	0.125 W/m-K	0.868 BTU-in/hr-ft <sup>2</sup> -°F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 0.040	<= 0.040	STI 3063/3161

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.050 %	<= 0.050 %	STI 3062

Descriptive Properties	Value	Comments
Composition	Na & K	<7 ppm, STI 3038
Hydroxyl Number	61 - 67 mg KOH/g	STI 3007/3162

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China