

BASF Procom® D 1026 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Procom-D-1026-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Linear Mold Shrinkage, Flow	0.015 cm/cm	0.015 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.0 MPa	4210 psi	
Elongation at Break	20 %	20 %	
Tensile Modulus	2.00 GPa	290 ksi	
Charpy Impact Unnotched	3.50 J/cm ²	16.7 ft-lb/in ²	
	1.00 J/cm ²	4.76 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	115 °C	239 °F	
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	
Vicat Softening Point	100 °C	212 °F	
Flammability, UL94	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China