

## BASF Procom® D 1165 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Procom-D-1165-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Procom-D-1165-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.0080 cm/cm	0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.0 MPa	2900 psi	
Elongation at Break	20 %	20 %	
Tensile Modulus	2.00 GPa	290 ksi	
Charpy Impact Unnotched	NB	NB	
	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 µm/m-°C	50.0 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	103 °C	217 °F	
Deflection Temperature at 1.8 MPa (264 psi)	59.0 °C	138 °F	
Vicat Softening Point	55.0 °C	131 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China