

**BASF Procom® GC20H 250 Polypropylene**

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Uses: car and truck fans and shrouds, car rear light housings, car radiator expansion tanks, car grills, domestic appliance components (e.g. washing machine tanks, impellers housings, etc.), textile bobbins and chemical plant, furniture frames. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Procom-GC20H-250-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Procom-GC20H-250-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	70.0 MPa	10200 psi	
Elongation at Break	3.0 %	3.0 %	
Tensile Modulus	4.70 GPa	682 ksi	
Charpy Impact Unnotched	3.50 J/cm <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	
	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C	22.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	
Deflection Temperature at 1.8 MPa (264 psi)	142 °C	288 °F	
Vicat Softening Point	130 °C	266 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China