

BASF Procom® GC30S 403 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Uses: Electrical appliance housings (e.g. drills), components requiring high impact and temperature resistance, furniture frames. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Procom-GC30S-403-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	61.0 MPa	8850 psi	
Elongation at Break	3.5 %	3.5 %	
Tensile Modulus	5.70 GPa	827 ksi	
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	
	5.50 J/cm ²	26.2 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 μm/m-°C	16.7 μin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	159 °C	318 °F	
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	
Vicat Softening Point	95.0 °C	203 °F	
Flammability, UL94	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China