

**BASF Sico® Fast Red L 3855 Color Additive**

Category : Other Engineering Material , Additive/Filler for Polymer

**Material Notes:**

Description: Naphthol-AS-red pigment with good fastness properties in full shade  
 Chemical Structure: Naphthol-AS-red  
 Suitable for: Waterborn systems, Acrylic-isocyanate systems, Acid curing system, Amine curing system and Airdrying systems.  
 Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Sico-Fast-Red-L-3855-Color-Additive.php](http://www.lookpolymers.com/polymer_BASF-Sico-Fast-Red-L-3855-Color-Additive.php)

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in <sup>3</sup>	
pH	4.0 - 6.0	4.0 - 6.0	
Specific Surface Area	37 m <sup>2</sup> /g	37 m <sup>2</sup> /g	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 5000 ohm-cm	>= 5000 ohm-cm	

Descriptive Properties	Value	Comments
Chemical Fastness (months)	Butylacetate	3
	Ethanol	4
	HCL 2%	5
	Methyl ethyl ketone	3-4
	Mineral spirits	4
	NaOH 2%	5
	Solvenon™PM	2-3
	Xylene	3
	Color	Red
Fastness to Overcoating	2-3	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**