

## BASF Styropor® BFL 322 EPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Expanded Polystyrene (EPS)

### Material Notes:

Description: Modified expandable polystyrene (EPS) containing approximately 3.75 – 3.95 wt% pentane as the blowing agent. Styropor BFL products are compatible with many anti-stat, mineral oil and color additives during processing. Intended uses: Block molding applications, especially suited for excellent surface cut appearance. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Styropor-BFL-322-EPS.php](http://www.lookpolymers.com/polymer_BASF-Styropor-BFL-322-EPS.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.640 g/cc	0.0231 lb/in <sup>3</sup>	
Density	0.0150 - 0.0800 g/cc	0.000542 - 0.00289 lb/in <sup>3</sup>	
Bead Size	0.600 - 1.20 mm	0.0236 - 0.0472 in	>97%

Processing Properties	Metric	English	Comments
Moisture Content	<= 1.2 %	<= 1.2 %	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Pentane Content	3.75 - 3.95%	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China