

BASF Styropor® BFL 422 EPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Expanded Polystyrene (EPS)

Material Notes:

Description: Modified expandable polystyrene (EPS) containing approximately 3.75 – 3.95 wt% pentane as the blowing agent. Styropor BFL products are compatible with many anti-stat, mineral oil and color additives during processing. Intended uses: Shape molding for thin walled applications with fast cycles and excellent surface finish requiring modified material. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Styropor-BFL-422-EPS.php

Physical Properties	Metric	English	Comments
Bulk Density	0.640 g/cc	0.0231 lb/in ³	
Density	0.0180 - 0.0650 g/cc	0.000650 - 0.00235 lb/in ³	
Bead Size	0.420 - 0.850 mm	0.0165 - 0.0335 in	>97%, 2% max <0.425

Processing Properties	Metric	English	Comments
Moisture Content	<= 1.2 %	<= 1.2 %	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Pentane Content	3.75 - 3.95%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China