

BASF Ultradur B 4300 G6 LS High Speed BK15045 30% Glass Filled PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultradur-B-4300-G6-LS-High-Speed-BK15045-30-Glass-Filled-PBT.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	ISO 1183
Viscosity Test	89 cm ³ /g	89 cm ³ /g	Viscosity number
Melt Flow	27 g/10 min @Load 2.16 kg, Temperature 250 °C	27 g/10 min @Load 4.76 lb, Temperature 482 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	140 MPa	20300 psi	5mm/min; ISO 527
Elongation at Break	2.5 %	2.5 %	5mm/min; ISO 527
Tensile Modulus	9.85 GPa	1430 ksi	1mm/min; ISO 527

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	10 K/min
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75

Descriptive Properties	Value	Comments
Color	BK15045	
Commercial Status	Active America	
Impact Modified	No	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China