

BASF Ultradur® B 4406 G2 10% Glass Filled PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 10% Glass Fiber Filled

Material Notes:

Description: Is a PBT, flame-retardant injection-molding grades, with 10% glass fibers, for parts requiring enhanced fire resistance, e.g. plug-and-socket connectors, housings, coil formers and lighting components. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultradur-B-4406-G2-10-Glass-Filled-PBT.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183
Water Absorption	0.40 %	0.40 %	Saturation; DIN 53495/1L
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C; 50% RH
Viscosity Measurement	120	120	[ml/g]; Viscosity number; ISO 1628
	70	70	20 mins plasticating
	@Temperature 290 °C	@Temperature 554 °F	
	75	75	30 mins plasticating
	@Temperature 280 °C	@Temperature 536 °F	
	75	75	10 mins plasticating
	@Temperature 300 °C	@Temperature 572 °F	
	90	90	30 mins plasticating
	@Temperature 270 °C	@Temperature 518 °F	
	95	95	10 mins plasticating
@Temperature 290 °C	@Temperature 554 °F		
100	100	5 mins plasticating	
@Temperature 300 °C	@Temperature 572 °F		
100	100	30 mins plasticating	
@Temperature 260 °C	@Temperature 500 °F		
105	105	10 mins plasticating	
@Temperature 280 °C	@Temperature 536 °F		
106	106	30 mins plasticating	
@Temperature 250 °C	@Temperature 482 °F		
110	110		

Physical Properties	Metric @ Temperature 270 °C	English @ Temperature 518 °F	10 mins plasticating Comments
	115 @Temperature 260 °C	115 @Temperature 500 °F	10 mins plasticating
	115 @Temperature 240 °C	115 @Temperature 464 °F	30 mins plasticating
	117 @Temperature 250 °C	117 @Temperature 482 °F	10 mins plasticating
	120 @Temperature 240 °C	120 @Temperature 464 °F	10 mins plasticating
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	Sheet
Linear Mold Shrinkage, Transverse	0.013 cm/cm	0.013 in/in	Sheet
Melt Flow	22.5 g/10 min @Load 2.16 kg, Temperature 250 °C	22.5 g/10 min @Load 4.76 lb, Temperature 482 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	95.0 MPa	13800 psi	50 mm/min; ISO 527-2
Elongation at Break	3.3 %	3.3 %	50mm/min; ISO 527-2
Modulus of Elasticity	5.50 GPa	798 ksi	ISO 527-2
Charpy Impact Unnotched	3.00 J/cm ² @Temperature -30.0 °C	14.3 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	3.00 J/cm ² @Temperature 23.0 °C	14.3 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.600 J/cm ² @Temperature 23.0 °C	2.86 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Dart Drop, Total Energy	<= 5.00 J	<= 3.69 ft-lb	W₅₀₁ housing; ISO 6603-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 µm/m-°C @Temperature 23.0 - 80.0 °C	27.8 µin/in-°F @Temperature 73.4 - 176 °F	DIN 53752
Specific Heat Capacity	1.60 J/g-°C	0.382 BTU/lb-°F	IEC 1006

Thermal Properties	Metric	English	Comments
Melting Point	220 - 225 °C	428 - 437 °F	050, ISO 11357-3
Maximum Service Temperature, Air	120 °C	248 °F	at 50% loss of tensile strength after 20000h; IEC 216-1
	130 °C	266 °F	at 50% loss of tensile strength after 5000h; IEC 216-1
	210 °C	410 °F	
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75-2
Decomposition Temperature	>= 290 °C	>= 554 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 93
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 93
Dielectric Constant	3.5	3.5	IEC 250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.5	3.5	IEC 250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	40.0 kV/mm	1020 kV/in	IEC 243/1
Dissipation Factor	0.0080	0.0080	IEC 250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.015	0.015	IEC 250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	150 V	150 V	Test solution B; IEC 112
	225 V	225 V	Test solution A; IEC 112

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties ^{ref}	Metric	English	Comments ^{not}
Zone 1	240 °C	464 °F	Feeding zone
Zone 2	245 °C	473 °F	Compression
Zone 3	250 °C	482 °F	Metering-zone
Zone 4	250 °C	482 °F	Nozzle
Melt Temperature	250 °C	482 °F	Optimal
	260 °C	500 °F	for shrinkage test
	250 - 275 °C	482 - 527 °F	Injection-molding
Mold Temperature	60.0 - 100 °C	140 - 212 °F	
	80.0 °C	176 °F	for shrinkage test, Optimal
Drying Temperature	80.0 - 120 °C	176 - 248 °F	
Dry Time	4 hour	4 hour	

Descriptive Properties	Value	Comments
Color	Natural, Colored, Black and Special Colors	
Commercial Status	Europe	
Ignition Temperature	>350°C	ASTM D1929
Peripheral screw speed	<0.25 m/s	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China