

**BASF Ultradur® B 4406 G3 Uncolored Q717 PBT**

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

**Material Notes:**

Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Ultradur-B-4406-G3-Uncolored-Q717-PBT.php](http://www.lookpolymers.com/polymer_BASF-Ultradur-B-4406-G3-Uncolored-Q717-PBT.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.600 - 0.900 g/cc	0.0217 - 0.0325 lb/in <sup>3</sup>	
Density	1.60 - 1.70 g/cc	0.0578 - 0.0614 lb/in <sup>3</sup>	ISO 1183

Thermal Properties	Metric	English	Comments
Melting Point	220 - 230 °C	428 - 446 °F	DIN 53736
Decomposition Temperature	>= 290 °C	>= 554 °F	

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Ignition Temperature	>350°C	ASTM D1929

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China