

BASF Ultraform® FK 61002 20% Carbon Black Filled POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Description: Polyoxymethylene based batch with approx. 20% carbon black for coloring thermoplastic polyoxymethylenes. Recommended concentrations of FK61002 batch within the mixture with thermoplastic polyoxymethylenes are in the range of 1 to 2 %. Higher concentrations (up to 10 %) may yield further improved UV stability but will reduce toughness. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultraform-FK-61002-20-Carbon-Black-Filled-POM.php

Physical Properties	Metric	English	Comments
Bulk Density	0.890 g/cc	0.0322 lb/in ³	
Density	1.40 g/cc	0.0506 lb/in ³	DIN 53479
Melt Flow	35 g/10 min @Load 10.0 kg, Temperature 190 °C	35 g/10 min @Load 22.0 lb, Temperature 374 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 11357-1/-3
Decomposition Temperature	>= 240 °C	>= 464 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 230 °C	374 - 446 °F	Injection molding

Descriptive Properties	Value	Comments
Color	Black	
Commercial Status	Europe	
Ignition Temperature	320 - 340 °C	ASTM D1929

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China