

BASF Ultramid® 1310-11 NF2001 PA66 (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Ultramid 1310-11 NF2001 is a controlled crystallization, fast cycling PA6/6 which provides extremely fast cycle times and improved productivity over Ultramid 1000.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-1310-11-NF2001-PA66-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	dry; ISO 1183
Water Absorption	8.5 %	8.5 %	beginning dry; ISO 62
Moisture Absorption at Equilibrium	2.5 %	2.5 %	beginning dry (23°C/50% R.H.); ISO 62
Linear Mold Shrinkage	0.016 cm/cm	0.016 in/in	ASTM Data; MD

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	69.0 MPa	10000 psi	50mm/min; ISO 527
Elongation at Break	>= 50 %	>= 50 %	50mm/min, Nominal strain; ISO 527
Elongation at Yield	20 %	20 %	50mm/min; ISO 527
Tensile Modulus	1.80 GPa	261 ksi	1mm/min; ISO 527
Flexural Modulus	1.50 GPa	218 ksi	ISO Data
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	ISO Test
Charpy Impact Unnotched	NB	NB	ISO 179
	NB	NB	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.40 J/cm ²	6.66 ft-lb/in ²	ISO 179
	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	257 °C	495 °F	10 K/min
	257 °C	495 °F	ASTM Test

Descriptive Properties	Value	Comments
Color	Natural	
Commercial Status	Active America	
Impact Modified	No	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China