

BASF Ultramid® A24 E 01 PA66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-A24-E-01-PA66.php

Physical Properties	Metric	English	Comments
Bulk Density	0.700 g/cc	0.0253 lb/in ³	
Density	1.12 - 1.15 g/cc	0.0405 - 0.0415 lb/in ³	ISO 1183

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	DIN 53765
Decomposition Temperature	>= 300 °C	>= 572 °F	

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Ignition Temperature	>400°C	ASTM D1929

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China